

2010
2011
2012
2013

CABERNET SAUVIGNON | 20XX
VALLE CENTRAL

Discovery. Adventure. The thrill of something new. Epica is about experiencing more. It's about moments: getting together with friends and sharing spirited conversation, good food, and great wine. This Chilean Cabernet Sauvignon is filled with rich flavors of blackberry and raspberry jam with a generous smooth finish worth savoring.

Eco-Friendly Winemaking • www.be360.cl

IMPORTED BY SHAW-ROSS INTERNATIONAL IMPORTERS, MIRAMAR, FLORIDA

WINE PRODUCED AND BOTTLED BY VINA SAN PEDRO S.A., MOLINA-CHILE

GOVERNMENT WARNING: (1) ACCORDING TO THE SURGEON GENERAL, WOMEN SHOULD NOT DRINK ALCOHOLIC BEVERAGES DURING PREGNANCY BECAUSE OF THE RISK OF BIRTH DEFECTS. (2) CONSUMPTION OF ALCOHOLIC BEVERAGES IMPAIRS YOUR ABILITY TO DRIVE A CAR OR OPERATE MACHINERY, AND MAY CAUSE HEALTH PROBLEMS.

WINE OF CHILE
ENVASADO EN CHILE

CONTAINS SULFITES

ALC. XX.X% BY VOL. 750 ML

EPICAWINES.COM



Nro de Lote / Lote Number

UPC

0 88320 13501 5

12
12.5
13
13.5
14
14.5

Medidas: 80 x 97

Barniz: Mate

Papel: Cameo Diamond Crest WS OPP

Sist. de Imp: AA

Colores

 Negro

 Cool
Gray 9

 Especial
(crema)

MATRIZ ETIQUETAS AUTOADHESIVAS			
Cliente: Viña S.P.T.		Fecha	20-dic-11
Imprenta: Colorama	Etiqueta	EPICA C.S.	
Papel Etiqueta	Papel C/Etiqueta	P.Respaldo	
Cameo Diamond Crest WS	Cameo Diamond Crest WS	PET	

Dimensiones Etq. Superficie Peso Gramaje Espesor	Códigos	V2090765	V2090766			
		Parámetros				
	Magnitudes	Etiqueta	C/Etiqueta	P.Respaldo		
	cm	9,56 X 13,6	8 X 9,7			
	cm2	130	77,6			
	grs.	1,896	1,148			
	grs/m2	145,85	147,94	42,65		
	mm	0,17	0,14	0.03		
Temp.Reactivación	°C	> 6	> 6		Humd. %	Temp. °C
Adherencia Inicial temp. Ambiente	grs./fuerza	< 500	> 500		54	22,9
Adherencia Inicial 6 °C	grs./fuerza	< 160	> 160			
Adherencia 48 hrs. Temp Ambiente	grs./fuerza	> 500	> 500			
Adherencia 48 hrs. 6 °C	grs./fuerza	> 500	> 500			
Rasgado en seco Papel Respaldo	grs./fuerza			NA		
Rigidez	Ángulo	157	150			
Resistencia Agua hielo	> 24 hrs.	> 24	> 24			
Defor. Superficial Humedad Ambiente	P - NP	NP	Np		P = Presenta NP = No Presnta NA= No Aplica	
Defor. Superficial Humedad Forzada	P - NP	NP	NP			
Opacidad	P - NP	P	P			
Bloking	P - NP	NP	Np			

Observaciones

- * La etiqueta por su gofrado pierde un porcentaje de adhesrencia pero no es de preocupación
- * El repaldo de Etiqueta es un film PET
- * Su opacidad es leve y no constituye preocupación

Aprobada

Jorge Córdova M.