


TECHNICAL SPECIFICATIONS

Bag Type: PROPRE of 0002_L Size: 320 *200

Code article: 1669585 or B0002L197P (Old code article) Reference: 2L WLxE/amkFa/VTUpiR-1 (320*200)

DIMENSIONS (IN MM):

Bag	Dimensions	Tolerances
Length L	320	-5/+ 5
Width 1	200	-5/+ 5



Spout n°1	Dimensions	Tolerances
Position from spout centre to bottom seal or to bottom perforation (G1 or R)	279,0	-5/+ 5
Position from spout centre to	55,0	-8/+ 8
the left side (f1)		
Inside spout diameter	28,20	
Outside diameter (for filling	33,00	
machine pincers)		
Height	19,00	

BAG WEIGHT:

Bag gross weight	0.040 KG	
Dug gross weight	0.040 10	

BAG CONSTRUCTION - MATERIALS:

Bag	Outer Film	Inner Film
Material based on	EVOH	PE
Thickness (in µm)	90	80
Colour	NATUREL	NATUREL
O² permeability at 23℃		
and 75% RH - (ASTM F1927 / D3985)	2	NON_SIGNIFICATIF
(CC/M2/24H/Atm under 100% O ²)		
(on new material before bag production)		

	No	Yes
Irradiation	X	
Web bag		X
If web bag, perforation	6,10	
type (in mm)		

Spout (gland)	Spout n'1
Type	SHORT
Material	LDPE
Colour	IVOIRE

Marquage	
Type	

Closure	Closure nº 1
Type	VT UNO
Material	PP ELASTOMERE
	HDPE HDPE
Colour	NATUREL WHITE
	RED RED
Pre-set position (bef	Fore filling) 1ST NOTCH
Orientation	12H00

08 10 24

Approved by R &D on the 08.10.2024

Printed the : 08.10.2024

RD EN 004C-03/07/17

 $\begin{array}{lll} \text{Revision} & : & 0 \\ \text{Page} & : & 1 \text{ out of } 2 \end{array}$



TECHNICAL SPECIFICATIONS

Bag Type: PROPRE of 0002_L Size: 320*200

 $\textbf{Code article: } 1669585 \text{ or } B0002L197P \text{ (Old code article)} \\ \textbf{Reference: } 2L \text{ } WLxE/amkFa/VTUpiR-1 \text{ } (320*200) \\$

PACKAGING / TRANSPORT :

	Type	Dimension	Contents	Weight
		(in mm)	(in Bags)	(in kg)
Box	MOBITAINER	0*0*0	2.500	107,130
Pallet	EUROPE NIMP 15	800*1.200	5.000	239,260

REMARKS:

Food Contact: Refer to the declaration of conformity.

Identification: Each bag is identified with SK BIB, volume, production order number, production day, time, bag number and a food safe symbol.

Storage: Empty Bags have to be stored at room temperature, in a clean, dry and dust free area, packed in their original carton and closed. Keep bags away from poisonous articles, heat sources, smelly products and direct sun. Optimal conditions of storage are comprised between 15-25°C and 40-60% of relative humidity. Unfilled empty bags canbe stored during a short period at +0°C mini and +30°C maxi, but must bestored in ambient conditions 24 to 48 h before use.

<u>Lise period</u>: It is expected that bags will be suitable for use 24 months from the date of production, provided that the storage and warehousing conditions detailed above are adhered to. We advise a First In/First Out (FIFO) inventory control system.

If this time period is exceeded, Smurfit Kappa Bag-in-Box Technical services must be contacted prior to use.

 $\underline{\underline{Filling}}$: The bag is to be filled to its nominal volume.

Smurfit Kappa Bags are suitable for product filled at temperature between +0°C and 40°C. Outside this temperature range, please seek technical assistance from Smurfit Kappa Bag-in-Box and refer to our GMP guidelines and Food Contact Declaration specific per application.

The outer-packaging must be suitable to the dimension of the bag: no excess free space should exist between the filled bag and its outer packaging. For bags more than 200L, the viscosity has to be above 1000 cPoises at $20^{\circ}C$.

Transport: Product must be shipped at temperature above +0°C.

Palletization: Pallets should not be stacked during transport and storage.

Height of pallet of 12 boxes: 1.97 m Height of pallet of 14 boxes: 2m 28 Height of 2 mobitainers: 1,87 m $\,$

The guarantee for SKBIB products is limited to the reimbursement or the replacement of products that are jointly recognized as defects. This guarantee excludes all the fees, compensations and damages. The current tehrnical specifications are provided for information purposes and cannot be held against their issuer.

This document cancels and replaces the previous document.

: 08.10.2024

Approved by R &D on the 08.10.2024

Creation Date : Revision : 0

RD EN 004C-03/07/17

Printed on the

Page : 2 out of 2